



Moroccan Wall Finish

To create this finish on a 8'x10" wall (80 sq. ft.) you need:

- 2 quarts of Venetian Plaster Pre-Mixed Master Palette Color Adobe (VP4000).
- 2 quarts of Metallic Paint – Burnt Orange
- 1 quart Platinum Wall Glazing Cream
- 1 4oz bottle of each Glazing Cream Color: Aged Mahogany, Eggplant and Coffee Bean.
- 1 Alhambra Stencil
- 1 Japanese Stainless Steel Trowel
- 2 4oz bottles of Extender for Rolling
- 1 Metallic Paint Roller
- 1 quart MasterClear Topcoat - High Gloss

Step-by-Step

1. Prime surface with an acrylic primer or paint with a low sheen acrylic paint and allow to dry per manufacturer's instructions.
2. Trowel on a thin skim coat of Venetian Plaster over entire surface and allow to dry.
3. Once dry, trowel on another thin layer over entire surface. Leave a subtle profile on the finish and allow to dry.
4. Place stencil in center starting point and affix with low tack tape.
5. Apply Venetian Plaster through stencil using the trowel. Be sure to cover the entire stencil image, leaving irregularities when applying to add to the character of the finish. Remove stencil and allow to dry. Repeat until all desired areas have been stenciled.
6. Apply first coat of Metallic Paint over entire surface per label instructions and allow to dry.
7. Apply a second coat of Metallic Paint and allow to dry for at least 8 hours. Depending on color choice a third coat may be necessary. For this finish a third coat was applied and allowed to dry.
8. Mix a quart of Platinum Wall Glazing Cream into a larger container. Tint this with 4oz Aged Mahogany, 8 tsp Eggplant and 8 tsp Coffee Bean Glazing Cream Colors and stir mixture thoroughly.
9. Working in 4'x4' areas, roll on a uniform coat of the tinted Wall Glazing Cream. While wet, wipe the surface with a jersey cotton rag or cheesecloth to remove glaze and reveal raised surfaces. Repeat until entire surface is complete and allow to dry.
10. If a protective topcoat is necessary, use MasterClear Protective Topcoat in desired sheen. High Gloss was used for this finish. Allow glazed finish to dry for 48 to 72 hours prior to top coating.