TECHNICAL DATA



MODERN MASTERS®

METALLIC PAINT COLLECTION MASTERCLEAR TOPCOAT

DESCRIPTION AND USES

Modern Masters[®] MasterClear[®] is a single component water based aliphatic acrylic polyurethane that provides an extremely durable protective topcoat to be used over Modern Masters Metallic Paint Collection products without affecting their metallic shimmer. This unique protective clear topcoat product utilizes self-cross linking technology and UV absorbers and inhibitors that make the product extremely mar resistant and suitable for exterior use. MasterClear is available in satin or semi-gloss sheens and comes in both quarts and gallons.

NOTE: Other clear topcoats may dull and otherwise ruin the shimmering appearance of Metallic Paint Collection paints.

This product can only be sold as a part of a Faux Finishing coating system.

PRODUCT FEATURES AND BENEFITS

- User friendly water based, single component and dries to the touch in 30 minutes
- Extremely durable abrasion and mar resistant clear protective topcoat
- Will not affect the metallic shimmer of the Metallic Paint Collection products
- UV resistant and non-yellowing finish suitable for interior and exterior use
- VOC compliant nationwide

PRODUCTS

32 Oz.	GALLON	DESCRIPTION
ME66432	ME664GAL	Satin
ME66232	ME662GAL	Semi-Gloss

PRODUCT APPLICATION

SURFACE PREPARATION

Allow Metallic Paint Collection colors to dry for 24-48 hours before applying MasterClear. Painted surface should be clean, dry and fully cured prior to application. For surfaces not painted with Modern Masters Metallic Paint Collections colors, apply on a small test area to ensure the color and desired effect is achieved.

APPLICATION

Modern Masters Metallic Paint Collection MasterClear can be brushed, rolled, or spray applied Stir thoroughly before use, do not shake. For best results and maximum protection, it is recommended to apply two or more coats for interior use and three or more coats for exterior use.

Do not apply in temperatures below 55°F/13°C or above 95°F/35°C.

BRUSHING: Use a high-quality synthetic bristle brush.

PRODUCT APPLICATION (cont.)

APPLICATION (cont.)

ROLLING: Use a high-quality short nap varnish roller.

SPRAYING: To spray MasterClear, thin with up to 10%, 12 fluid ounces of water to one gallon of MasterClear Topcoat. Use an HVLP gun, conventional cup gun or airless spray system.

TAPING: Use high quality, low-tack tape when taping over surfaces that have been previously painted with Metallic Paint. When painting over taped-off areas be aware that Metallic Paints exhibit poor early adhesion properties and are elastomeric (they stretch) during curing. Because of these two factors consider cutting along the tape edge with a razor blade to avoid delaminating the fresh paint from the substrate.

DRY TIMES: Drying times were recorded at 77°F and 50% RH. Dry-to-touch time is approximately $\frac{1}{2}$ hour. Recoat time is approximately 2 hours and full cure in 7 days.

NOTE: Lower temperature and/or higher humidity will lengthen the dry and cure times.

COVERAGE: One gallon will cover approximately 320 square feet. Approximately 1.5 mils dry film thickness per coat. Minimum of two coats is recommended.

SHEEN RANGES @ 60°: Satin 20-30 and Semi-Gloss 50-65

CLEAN UP: Clean brushes, rollers, tool, and equipment with soap and warm water immediately after use. Do not reuse containers and properly dispose of empty containers.

HANDLING & STORAGE: Close tightly all containers when not in use. Store in a cool dry place away from direct sunlight. Do not freeze.

DISPOSAL: Dispose of unused or unwanted product in accordance with local laws regulating water-based coatings.



TECHNICAL DATA

MDM-02

MODERN MASTERS®

METALLIC PAINT COLLECTION MASTERCLEAR TOPCOAT

PHYSICAL PROPERTIES

		METALLIC PAINT COLLECTION MASTERCLEAR TOPCOAT
Resin Type		Aliphatic acrylic polyurethane
Weight	Per Gallon	8.63-8.67 lbs.
	Per Liter	1.03-1.04 kg
Solids	By Weight	32.03-32.93 %
	By Volume	29.71-30.30 %
Volatile Organic Compounds		<100 g/l
Recommended Dry Film Thickness (DFT) per Coat		1.5 mils
Wet Film to Achieve DFT (Unthinned material)		5 mils
Practical Coverage at Recommended DFT (assume 15% material loss)		Up to 320 sq.ft./gal.
Dry Times at 77°F (25ºC) and 50% Relative Humidity	Touch	30 minutes
	Recoat	2 hours
	Full Cure	7 days
Shelf Life		5 years
Flash Point		144°F (62°C)
Storage		PROTECT FROM FREEZING
Safety Information		For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.



Rust-Oleum Corporation 11 Hawthorn Parkway Vernon Hills, Illinois 60061

Phone: 800.942.3166 www.modernmasters.com