

HMIS RATINGS

Health	2
Flammability	4
Physical Hazard	0

Modern Masters Inc.
Los Angeles, CA USA
(800) 942-3166
modernmasters.com

© 2015, Modern Masters Inc.
Made in USA



colorfast™

non-fading


EX ZERO VOC

acrylic polyurethane

clear base (component A)

industrial use only
by professional, trained painters.
not intended for sale to or use by general public.

0.75 US Gal. / 2.83 L



Use Colorfast EX Colorants for maximum exterior durability and colorfastness, while maintaining the formulated ZERO VOC SCAQMD “Super Compliancy” rating

Meets all categories of SCAQMD Rule 1113 - Architectural Coatings Rules 1107, 1136, 1145, 1151

COVERAGE COBERTURA
700-800 at 1 mil DFT
sq ft / gal pies cuadrados / gal
1.8-3.0 DFT required depending upon color
1.8-3.0 DFT requerido dependiendo del color

IMPORTANT: The contents of this package must be blended with components before the product can be used. Follow all mixing and thinning instructions below. Before opening the packages read all warning labels, SDS and TDS information. It is recommended to review applicable state and local regulations before using product. Follow all precautions recommended for use of this product.

MIXING AND THINNING INSTRUCTIONS: This is a two-component paint system. First, mix each component thoroughly. Open the Activator (component B) carefully. Do not open if container is bulged. Discard if container is bulged or product is not clear. Then add 3 parts of Acrylic Polyurethane Base (component A) to 1 part Activator (component B) by volume and mix product thoroughly. Mix only the number of kits that can be used within 1-2 hours.

Properly mixed product is ready to apply by brush, roller or spray equipment. The initial viscosity is 25-35 seconds Zahn #2 Cup. Sprayable pot-life is 2-3 hours @ 77°F (25°C). If further reduction is desired, add up to 25% of Colorfast EX ZERO VOC Reducer. To speed up dry time, add 1/2 ounce to 2 ounces of Colorfast EX ZERO VOC Accelerator. NOTE: This will decrease the sprayable pot-life. Do not use with other manufacturers' additives. Keep containers tightly closed when not in use. Do not contaminate product with alcohol or water.

PREPARATION FOR PAINTING: The surface to be coated shall be clean (free of oil, dust, etc.). Metal surfaces should be primed with one of Modern Masters recommended low VOC epoxy or polyurethane primers or primer surfacers. Consult your technical representative for preparation, application and substrate specific details. Spray equipment must be properly grounded. Clean equipment immediately after use with thinner (SCAQMD compliant equipment cleaner). Production type operations and field application shall be performed only in specifically designated areas with local exhaust ventilation and other environmental control measures as required by OSHA on the basis of an on-site industrial hygiene survey. Touch-up

Drying Time <i>Tiempo de Secado</i> @ 70% RH	70-85°F	
	Dry-to-Touch: 2-4 hrs Recoat: 2-48 hrs Dry Hard: 6-10 hrs	<i>Tacto: 2-4 horas</i> <i>Repintar: 2-48 horas</i> <i>Tacto Duro: 6-10 horas</i>
Temperature and humidity dependent <i>Dependiente de temperatura y humedad</i>		

type operations shall be performed only in areas with good general ventilation. Do not expose unprotected personnel in adjacent areas to mist, spray, or vapor.

CONTAINS: PCBTF CAS# 98-56-6
Acetone CAS# 67- 64-1

HEALTH & SAFETY: Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal. **MAYBE HARMFUL IF ABSORBED THROUGH SKIN.** Wear protective gloves/protective clothing/eye protection/face protection. Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. Do not smoke. Extinguish all flames and pilot lights and turn off stoves, heaters, electric motor and other sources of ignition during use and until vapors are gone. In case of fire, use Alcohol Film Forming Foam, Carbon Dioxide, Dry Chemical, Dry Sand, Water Fog to extinguish. Prevent build-up of vapors by opening all windows and doors to achieve cross ventilation. **USE ONLY OUTDOORS OR WELL-VENTILATION AREA.** Do not breathe vapors or mist. Ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness, or if air monitoring demonstrates vapor/mist level above applicable limits, wear an appropriate properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin, and clothing. Wash thoroughly after handling.

FIRST AID: If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. **EYE CONTACT:** Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing and get medical attention; **IF ON SKIN (or hair):** Take off immediately all contaminated clothing. Rinse skin with water/shower. **INGESTION:** If swallowed, call POISON CENTER or doctor/physician. If spilled, contain spilled material and remove with inert

absorbent. Dispose of contaminated absorbent and excess material in accordance to local, state, and federal regulations and ordinances. Do not allow to enter waterways, wastewater, soil, storm drains or sewer systems.

PROP 65 WARNING! This product contains a chemical known to the State of California to cause cancer, birth defects, or other reproductive harm.

RECOMMENDED STORAGE TEMPERATURE: Store indoors at 50°- 95°F ((10°-35°C). Store in a well-ventilated place. Keep cool.

Flash Point (TCC): -4°F (-20°C).

DOT INFORMATION: Paint: Flammable Liquid 3; Packing Group II, UN-1263



DANGER!
HIGHLY FLAMMABLE LIQUID AND VAPORS
MAY CAUSE FLASH FIRE

EXPOSURE TO VAPORS CAUSES LUNG, SKIN, OR EYE IRRITATION

KEEP OUT OF REACH OF CHILDREN

AIR QUALITY INFORMATION

This product as supplied meets VOC content limits of SCAQMD Rules 1113, 1107, 1136, 1145, 1151.

Colorfast Base only formulation data:

Coating VOC Content: 0 g/L (0 lb/gal)
Material VOC Content 0 g/L (0 lb/gal)

Catalyzed Material formulation data:

Coating VOC Content: 0 g/L (0 lb/gal)
Material VOC Content 0 g/L (0 lb/gal)

Non-Photochemically Reactive

This product does not contain t-Butyl Acetate (tBAC)

This product contains
No Hazardous Air Pollutants