



**MODERN MASTERS®
VENETIAN PLASTER TOPCOAT**

DESCRIPTION AND USES

Modern Masters® Venetian Plaster Topcoat is used as a protective sealer over a dry Venetian Plaster finish. High traffic areas where washability is imperative or rooms that experience high humidity, such as bathrooms, should be sealed with Venetian Plaster Topcoat.

NOTE: Other protective topcoats cannot be used to protect the Venetian Plaster.

PRODUCT

32 Oz.	DESCRIPTION
VP300QT	Satin Venetian Plaster Topcoat

PRODUCT APPLICATION

SURFACE PREPARATION

After sanding or burnishing the Venetian Plaster, wipe the surface with a clean damp rag to eliminate any dust. Allow the surface to dry.

APPLICATION

NOTE: Always test the product in a small, inconspicuous area before beginning a project. We recommend preparing a sample board prior to beginning a project to check color and technique. The paint should be mixed thoroughly before using.

Venetian Plaster Topcoat is applied using Modern Masters Japanese Trowel or a putty knife. It cannot be rolled, brushed or sprayed on.

Hold the trowel at a 60° angle and scrape a very thin layer of the topcoat onto the dry Venetian Plaster finish. Scrape off any excess using a clean trowel and let this coat dry.

This application will slightly darken the color and will dry to a satin sheen. The topcoat can be slightly polished once it is dry by burnishing with the edge of your trowel or the flat side of a clean putty knife.

PRODUCT APPLICATION (cont.)

TAPING: Use high quality, low-tack tape when taping over surfaces that have been previously painted. Therefore consider cutting along the tape edge with a razor blade to avoid delaminating the fresh paint from the substrate.

DRY TIMES: Dry time is approximately 1-2 hours. Dry time depends on thickness of application, temperature and humidity. (Drying times were recorded at 70°F and 50%RH)

NOTE: Lower temperature and/or higher humidity will lengthen the dry and cure times.

COVERAGE: One quart will cover approximately 140-155 sq. ft./13-14.m².

CLEAN UP: Clean tools with soap and warm water immediately after use. Do not reuse containers and properly dispose of empty containers.

HANDLING & STORAGE: Close tightly all containers when not in use. Store in a cool dry place away from direct sunlight. Do not store or apply in temperatures below 55°F/13°C. Do not freeze. If Venetian Plaster Topcoat becomes frozen, allow to completely thaw and come to room temperature before use. Stir thoroughly before use.

DISPOSAL: Dispose of unused or unwanted product in accordance with local laws regulating water-based coatings.

	TECHNICAL DATA	MDM-29
	MODERN MASTERS® VENETIAN PLASTER TOPCOAT	

PHYSICAL PROPERTIES

		VENETIAN PLASTER TOPCOAT
Resin Type		Water-based Acrylic
Pigment Type		Silica
Solvents		Water, glycol ethers
Weight	Per Gallon	8.75 lbs.
	Per Liter	1.03 kg
Solids	By Weight	24.31%
	By Volume	21.78%
Volatile Organic Compounds		102 g/l This product can only be sold as part of a Faux Finish coating system.
Recommended Dry Film Thickness (DFT) per Coat		0.5 mils
Wet Film to Achieve DFT (Unthinned material)		2.3 mils
Practical Coverage at Recommended DFT (assume 15% material loss)		140-155 sq. ft./qt.
Dry Times at 70-80°F (21-27°C) and 50% Relative Humidity	Touch	30 minutes
	Handle	1 hour
	Recoat	2 hours
	Full Cure	8 hours
Shelf Life		4 years
Flash Point		>200°F
Safety Information		PROTECT FROM FREEZING - NOT FREEZE THAW STABLE For additional information, see SDS

Calculated values are shown and may vary from the actual manufactured material.

The technical data and suggestions for use contained herein are correct to the best of our knowledge, and offered in good faith. The statements of this literature do not constitute a warranty, express, or implied, as to the performance of these products. As conditions and use of our materials are beyond our control, we can guarantee these products only to conform to our standards of quality, and our liability, if any, will be limited to replacement of defective materials. All technical information is subject to change without notice.